

BMI**WrapTec®**

Self-welding.
Watertight.
Weatherproof.


Chemical resistance of WrapTec

BMI Deutschland GmbH confirms the resistance or not resistance of the product WrapTec against the substances listed. Substances not listed have to be tested separately.

CHEMICAL	CONCENTRATION (%)	RESISTANCE
Acetone (C_3H_6O)	100	resistant
Aluminium chlorid ($AlCl_3$)	saturated	resistant
Benzine	-	not resistant
Bleach liquor ($NaClO$)	10	not resistant
Boric acid (H_3BO_3)	saturated	resistant
Calium chloride ($CaCl_2$)	saturated	resistant
Chlorine	marginal	not resistant
Chlorid acid ($HClO_3$)	20	not resistant
Chlorine water ($HOCl$)	saturated	not resistant
Diesel oil	100	not resistant
Glycerin ($C_3H_8O_3$)	100	resistant
Potassium chloride (KCl)	saturated	resistant
Caustic potash (KOH)	10	resistant
	60	not resistant
Copper sulphate ($CuSO_4$)	saturated	resistant
Table salt ($NaCl$)	saturated	resistant
Methanol (CH_3OH)	100	resistant
Nitrous exhaust fumes (NOx):	Trace	resistant
	higher concentration	not resistant
Oil (ethereous/ vegetable/ animale)	-	not resistant
	10	resistant
Hydrochloric acid (HCl):	30	not resistant
	concentrated	not resistant
Sea water	-	resistant
Sulphuric (H_2SO_4)	10	resistant
	50	not resistant
Tar	-	not resistant
Urin	-	resistant

BMI Group

BMI Deutschland GmbH, Frankfurter Landstraße 2 – 4, D-61440 Oberursel



Christian Sack
Sales Director BMI & Sales Excellence



Stefan Fleckenstein
Director Components Technology, RD&E